# PAPER DETAILS

TITLE: Investigation of Fractal Dimension Change in Synthesized CaSO4 Using PSSS

AUTHORS: Mücahit UGUR

PAGES: 72-79

ORIGINAL PDF URL: https://dergipark.org.tr/tr/download/article-file/520451



Received: 24 July 2018

Accepted: 1 August 2018

**Research Article** 

### Investigation of Fractal Dimension Change in Synthesized CaSO<sub>4</sub> Using PSSS

Mucahit Ugur<sup>\*a</sup>, Ozlem Dogan Aydeniz<sup>b</sup>, M. Muhtar Kocakerim<sup>a</sup>, M. Bora Akin<sup>a</sup>

<sup>a</sup>Çankırı Karatekin University, Chemical Engineering Department, Çankırı, Turkey

<sup>b</sup>Yıldız Technical University, Chemical Engineering Department, İstanbul, Turkey

\*Corresponding Author: m.ugur@karatekin.edu.tr

#### Abstract

Generally, commercial product of calcium sulfate anhydrous (CaSO<sub>4</sub>) is synthesized burning gypsum in kiln, in the process that the water is removed from gypsum crystallized by mixing CaCl<sub>2</sub> and Na<sub>2</sub>SO<sub>4</sub> in aqueous medium. It is possible to change gypsum properties by changing the parameters during crystallization. Also, the differentiation in the structures of the synthesized product can be possible with using additives during the crystallization. The changes in properties of these synthetically produced materials may be investigated instrumentally.

This study examines change of surface fractal dimensions ( $D_f$ ) of synthesized CaSO<sub>4</sub> anhydrate instrumentally. CaSO<sub>4</sub>.2H<sub>2</sub>O was synthesized by chemical precipitation method in the presence Poly(Sodium 4-Styrene Sulphonate) and measured N<sub>2</sub>-physisorption measurements after burning. Fractal dimensions were determined using single N<sub>2</sub>-adsorption/desorption isotherms method. For Fractal dimension calculations, the Frenkel–Halsey–Hill (FHH) and the Neimark–Kiselev (NK) methods were used. Taguchi method has been used in evaluation of experimental design for optimization of D<sub>f</sub> values.

Keywords: Frenkel-Halsey-Hill, Neimark-Kiselev, calcium sulfate

# 1. Introduction

It is easily perceived by man that a cube is three-dimensional and the square is two-dimensional. Length, height, thickness, area and volume can easily be calculated in these type materials. However, the materials in the nature are more complex in shape. When calculation of a kidney area is taken into account, more information than length, height and depth information is needed absolutely. The measure of the complexity of this formation is explained by the fractal dimension. In other words, fractal dimension is a measure of the complexity. It is derived from fractus word, which means "broken" in Latin. The entry of this definition into our life was possible by questioning the mathematician Benoit Mandelbrot's coastal length of England. At this point measurement can also be done through the map, or the circumference of the island is measured by help of a meter. Sensitivity can be further increased in this measurement: mm, nm, etc. As the sensitivity is increased, the measurement value will change. This is the result that the length of the measured of a finite piece is infinite can be said [1-7].

Dobrescu et al. reported that since 1984, it was reported that many studies on fractal geometry representing solid surfaces were made. In irregularly shaped materials, the fracture size value is between 2 and 3.  $D_f=2.0$  values, indicate regularity and smoothness and also  $D_f=3.0$  indicate highly irregular surface. The result obtained by using the SEM images in the study conducted and the result obtained by using the adsorption isotherm are very close to each other [5].

If it was easily described, calcium sulphate is a material that is being investigated for its ability to be used in processes such as dehumidification, or due to problems caused by shell formation in heat exchangers [8-9]. In this study, Df values were found by means of a program using adsorption isotherms. Using the Taguchi experimental design, in calcined calcium sulphate production, effect of production factors on fractal dimension has been revealed in the presence of Poly (Sodium 4-Styrene Sulphonate) (PSSS, Mw=1,000,000 g/mol) polymer. It is seen that, in the presence of PSSS, the most effective parameter on the fractal dimension is the  $[Ca^{2+}]/[SO_4^{2-}]$  ratio.

# Materials and methods

In the experiments, PSSS polymer was added to the calcium chloride solution. The amount of the PSSS was varied between 0.008 to 0.152 g/L. In this study, molecular weight of PSSS polymer was 1,000,000 g/mol and chemicals used were purchased from Sigma-Aldrich. For this study, Taguchi experimental method was selected and in design of experiment, four factors and three levels was used (Table 1). Taguchi L<sup>9</sup> orthogonal experimental design parameters are  $[Ca^{2+}]$  concentration,  $[Ca^{2+}]/[SO_4^{2-}]$  ratio, temperature, and [PSSS], respectively. The CaSO<sub>4</sub> samples were calcined in an oven at 500 °C for 5 hours. Quantachrome, Novatouch Lx<sup>4</sup> was used to obtain Isotherms. D<sub>f</sub> values were calculated from using obtained adsorption-desorption isotherms by TouchWin program (Fig. 1-2). Minitab program has been used to generate Taguchi Analyses.

# **Results and discussion**

The response table has been transferred to the Minitab program as it. First and second column were generated from adsorption isotherms, then third and fourth column were generated desorption isotherms. Result of this analysis is shown in Fig.3 and Fig. 4. By Frenkel-Halsey-Hill (FHH) and Neimark-Kiselev (NK) calculations, fractal dimensions obtained from isotherms

were used together in Taguchi analysis to understand the common effect. In Table 3, response table for signal to noise ratios is given. according to this table, the order of least effective parameter from the most effective parameter is as follows:  $[Ca^{2+}]/[SO_4^{2-}]$  ratio, Temperature (°C), [PSSS] (g/L), and  $[Ca^{2+}]$  concentration. In Fig. 3, main effects plot for means on Df value of changing parameters is analyzed Also, main effects plot for SN ratios on Df value of changing parameters is showed. (Figure 4)

### Conclusions

There are three major conclusions to be drawn:

-All samples of fractal dimension value were changed by used parameters in the presence of PSSS.

- While CaSO<sub>4</sub> is being synthesized to maximize the Df values; it should be applied the [PSSS] concentration of 0.08 g/L, the [Ca<sup>2+</sup>] concentration of 0.72 M, reactant ratio of 1, and the temperature of 20 °C then calcined at 500 °C for 5 hours.

- In the presence of PSSS, the most effective parameter on the fractal dimension is the  $[Ca^{2+}]/[SO_4^{2-}]$  ratio.

### Acknowledgements

We would like to thank Çankırı Karatekin University, Scientific Research Projects Coordination Unit for support to project number: MF200217B11.

# References

- 1 Rasband, S. N. "Fractal Dimension." Ch. 4 in Chaotic Dynamics of Nonlinear Systems. New York: Wiley, pp. 71-83, 1990.
- 2 Gori, U and M. Mari (2001) The correlation between the fractal dimension and internal friction angle of different granular materials, Soils and Foundations, 41, 3-4,17-23.
- 3 Pfeifer P., and Avnir D., (1983) Chemistry in noninteger dimensions between two and three. I. Fractal theory of heterogeneous surfaces. The Journal of Chemical Physics, 79, 3558.
- 4 Pfeifer, P., Farin, D., and Avnir D., (1983) Chemistry in noninteger dimensions between two and three. II. Fractal surfaces of adsorbents. The Journal of Chemical Physics, 79, 3566.
- 5 Dobrescu, G., Berger, D., Papa, F., Ionescu, N.I., Rusu M. (2003) Fractal analysis of micrographs and adsorption isotherms of La1-xSrxCoO3 samples. Journal of Optoelectronics and Advanced Materials, 5, 5, 1433-1437.
- 6 Khalilia, N.R., Pana, M., Sand, G., (2000) Determination of fractal dimensions of solid carbons from gas and liquid phase adsorption isotherms, Carbon 38, 573–588.
- 7 Lowell S., Shields J.E., Thomas M.A., Thommes M. (2004) Characterization of Porous Solids and Powders: Surface Area, Pore Size and Density. Particle Technology Series, vol 16. Springer.
- 8 Amjad, Z. and Demadis K.D. (2015) Mineral Scales and Deposits Scientific and Technological Approaches. Elsevier.

9 Doğan, Ö., Akyol, E. and Öner, M. (2004), Polyelectrolytes inhibition effect on crystallization of gypsum. Cryst. Res. Technol., 39: 1108-1114.

#### Figure and Table Captions



Figure 1. Absorption/desorption isotherm graph



Figure 2. Fractal dimension calculation graph in an isotherm



Figure 3. Main effects plot for means on  $D_f$  value of changing parameters



Figure 4. Main effects plot for SN ratios on Df value of changing parameters

	Α	В	С	D
Exp. No.	[Ca <sup>2+</sup> ] (mol/L)	[Ca <sup>2+</sup> ]/[SO <sub>4</sub> <sup>2-</sup> ] ratio	Temperature (°C)	[PSSS] (g/L)
Exp 1	0.24	0.5	20	0.008
Exp 2	0.24	1	30	0.08
Exp 3	0.24	2	40	0.152
Exp 4	0.48	0.5	30	0.152
Exp 5	0.48	1	40	0.008
Exp 6	0.48	2	20	0.08
Exp 7	0.72	0.5	40	0.08
Exp 8	0.72	1	20	0.152
Exp 9	0.72	2	30	0.008

Table1. Taguchi L<sup>9</sup> orthogonal experimental design

Table 2. Response Table

FHH (Adsorption)	NK (Adsorption)	FHH (Desorption)	NK (Desorption)
1.33900	3.06942	2.00249	3.37733
1.71322	3.04303	2.13883	3.33358
1.09386	3.02400	1.93424	3.39597
1.18291	3.01351	2.01280	3.40622
1.22604	3.01469	2.06868	3.43939
1.33420	3.04570	2.00450	3.34570
1.23817	2.95906	2.09806	3.42718
1.80132	3.05254	2.72737	3.41158
1.32860	3.06106	2.29518	3.46083

Level	Α	В	С	D
1	8.625	7.954	9.536	8.240
2	7.919	10.127	8.924	8.969
3	9.545	8.009	7.628	8.881
Delta	1.626	2.173	1.908	0.729
Rank	3	1	2	4

Table 3. Response Table for Signal to Noise Ratios Nominal is best (10. Log10(Ybar<sup>2</sup>/s<sup>2</sup>))